

# TEXTTEST

---

4207-1 Milgen Road, Columbus, GA 31907

Telephone: 844-309-6337

www.texttest.com

14295  
TexTesT Report: 14066  
Date: 4/21/23  
Page: 1 of 2

CLIENT:

**SUPACOLOR**

16918 Gramercy Place  
Gardena, CA 90247

ATTN: Luke Marsden

---

---

SAMPLE IDENTIFICATION:

PO # LM181122

SAMPLE :

SUPACOLOR IW TRANSFERS

CODE S-15376NB-46

---

---

ISO 15797:2017

Textiles — Industrial washing and finishing procedures for testing of workwear

Rating durability of print, Color Change.

Industrial Laundering: (Machine Wash 74°C, 60 minute cycle, Tumble Dry 63°C)

Rated every 5 cycles

SUPACOLOR

IW TRANSFERS

PASSED 50 Washes

TEXTTEST



Signed by

---

SAMPLE IDENTIFICATION: PO # LM181122  
SAMPLE :  
SUPACOLOR IW TRANSFERS  
CODE S-15376NB-46

---

ISO 15797:2017

Textiles — Industrial washing and finishing procedures for testing of workwear

Rating durability of print, Color Change.

Industrial Laundering: (Machine Wash 74°C, 60 minute cycle, Tumble Dry 63°C)

SUPACOLOR  
IW TRANSFERS

After 5 Launderings No Delamination  
No Color Change

After 10 Launderings No Delamination  
No Color Change

After 15 Launderings No Delamination  
No Color Change

After 20 Launderings No Delamination  
No Color Change

After 25 Launderings No Delamination  
No Color Change

After 30 Launderings No Delamination  
No Color Change

After 35 Launderings No Delamination  
No Color Change

After 40 Launderings No Delamination  
No Color Change

After 45 Launderings No Delamination  
No Color Change

After 50 Launderings No Delamination  
No Color Change